

**ISO 12924: L-XB(F)CAA2**  
**DIN 51502: K2K-20**



## PRODUCT DESCRIPTION

CLAYTEX HT 2 is a bentone clay thickened lubricating grease based on mineral oil. The grease contains antioxidants

The inorganic thickener, together with the special base oil blend, makes the product suitable for a wide range of applications that are lightly loaded, running at medium speed and in moderate temperatures.

CLAYTEX HT 2 is a multipurpose grease suitable for both industrial and automotive applications. The product's all-round properties make it a good option for various types of bearing applications running in lighter conditions

No dropping point  
 Wide range of use

## TYPICAL TECHNICAL DATA

Thickener		Clay
Base fluid		Mineral oil
Texture		Smooth
Colour	Visual	Brown
NLGI Grade	ASTM D 217 mod	2
Dropping point	IP 396	N/A
Base oil viscosity at 40°C	ASTM D 7152	180 mm <sup>2</sup> /s
Base oil viscosity at 100°C	ASTM D 7152	17 mm <sup>2</sup> /s
Penetration 60 strokes	ISO 2137	265 - 295
4-ball weld load	DIN 51350:4	2200 N
Water resistance at 90°C	DIN 51807:1	1
Water wash out at 38°C	ISO 11009	< 10 %
Emcor dist water	ISO 11007	> 1 - 1
Flow Pressure at -20°C	DIN 51805 mod	< 1400 mbar
SKF R2F B at 120°C	SKF	Pass
Density	IP 530	910 kg/ m <sup>3</sup>
Temperature range		-20°C to +160 °C (Max +180 °C)

The information above is based on current production data and can vary within given tolerances. Temperature range is given as a guideline only. Information and data can be changed without previous notification. This information replaces prior editions.